

Indorama Ventures Polymers Germany GmbH

5140

Polyethylene terephthalate

Polyester 5140 is specifically designed for the use in high tenacity spinning applications such as tire cord, airbags or other high strength fabrics. 5140 needs to be solid state polymerized (SSP) before its use in the applications mentioned above. If you are interested in an SSP'd version ready to use, please contact your Indorama representative.

Property	Typical Value
Intrinsic Viscosity (IV)	0.645 dl/g
TiO ₂	0.04 %

Please contact your Indorama representative for further technical information.

EU and FDA food contact statements are available upon request.

Please contact your Indorama representative to get more information on further regulatory statuses.

Product Data Sheet Disclaimer

This Product Data Sheet contains selected information about a specific Indorama Ventures Polymers Germany GmbH product, or group of products. THIS PRODUCT DATA SHEET DOES NOT CONTAIN A COMPLETE STATEMENT OF, AND DOES NOT CONSTITUTE A REPRESENTATION, WARRANTY OR GUARANTY WITH REGARD TO, A PRODUCT'S CHARACTERISTICS, USES, QUALITY, MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR THE SUITABILITY, SAFETY, EFFICACY, HAZARDS OR HEALTH EFFECTS OF THE PRODUCT, WHETHER USED SINGULARLY OR IN COMBINATION WITH ANY OTHER PRODUCT, EXCEPT TO THE EXTENT REQUIRED BY RELEVANT LAWS AND REGULATIONS.

Purchasers and users of the product are responsible for determining if the product is suitable for the intended use and that their workers and the general public are advised of any risks resulting from such use. Nothing contained in this Product Data Sheet shall be construed to modify any of the commercial terms pursuant to which the product was sold by Indorama Ventures Polymers Germany GmbH including, but not limited to, terms and conditions addressing each party's respective rights and obligations with regard to warranties, remedies and indemnification.